

JOURNAL OF EARTH ENERGY SCIENCE, ENGINEERING, AND TECHNOLOGY

HOME ABOUT LOGIN REGISTER SEARCH CURRENT ARCHIVES ANNOUNCEMENTS

Home > Vol 5, No 1 (2022)

JOURNAL OF EARTH ENERGY SCIENCE, ENGINEERING, AND TECHNOLOGY



Journal of Earth Energy Science, Engineering, and Technology (JEESET) has been established in 2018 by Master Program of Petroleum Engineering, Faculty of Earth Technology and Energy, Universitas Trisakti. ISSN of the Journal was issued by Pusat Dokumentasi dan Informasi Ilmiah (PDII) Lembaga Ilmu Pengetahuan Indonesia (LIPI) at the end of the year. The first publication was at the beginning of 2018. JEESET provides a medium for communication of information among the world's scientific and technological society. This journal intends to be of interest and utility to researchers and practitioners in the academic, industrial and governmental institutions. All research contributions of significant value related to earth energy science, engineering, and technology discipline are welcome. JEESET is an open access journal. This journal is consistently published three times per year. It has been accredited by Ministry of Research and Technology of the Republic of Indonesia No. 85/M/KPT/2020, April 3 2020, as 4th Rank (SINTA 4). It has also been listed in Index Copernicus International, Publons, Garuda, Crossref, ISJD, Base, PKP Index, Google Scholar, ResearchBib, ISSN, Indonesia Onesearch. In addition, it has already used Turnitin to prevent any suspected plagiarism in the manuscripts. For authors who wish to submit articles to this journal, please register as an author and then login to submit articles. Writing information and submit articles can be accessed in the author guidelines, and follow the instructions here. For further information, please contact the editorial secretariat at email: Jeeset_mtp@trisakti.ac.id

ANNOUNCEMENTS

CALL FOR PAPER

Dear Author and Reader, this journal is consistently published three times per year. The papers of this

Menu: Click here to Submit 1. Author Guideline 2. Focus and Scope 3. Ethics Statement 4. Editorial Team 5. Reviewer 6. Plagiarism Screening Policy 7. Mailing Address 8. Unique Visits



Journal Template Download Here

Journal of Earth Energy Science, Engineering, and Technology (JEESET) has been accredited by Ministry of Research and Technology of the Republic of Indonesia No. 85/M/KPT/2020, April 3 2020, as 4th Rank (SINTA 4). In addition, the journal has been listed in Index Copernicus International, Publions, Garuda, Crossref, ISJD, Base, PKP Index, Google Scholar, ResearchBib, ISSN, and Indonesia Onesearch. JEESET is an open access journal. The papers of this journal are available in Archives Section and free of charge for everyone to publish, read, and download.



Copyright (c) 2019 Journal of Earth Energy Science, Engineering, and Technology

Journal of Earth Energy Science, Engineering, and Technology (JEESET) has been indexed and listed in: inta4 Crossref INDEX COPERNICUS 6 ISJD INDONESIA ONESEARCH **PKP INDEX** RESEARCHEIE oublons PKP | INDEX oneSearch GARUDA **GOOGLE SCHOLAR** 155N Google BASE GARUDA CHAT MENDELEY turnitin 00 Program Studi Magister Teknik Perminyakan (Master of Petroleum Engineering) Fakultas Teknologi Kebumian dan Energi Universitas Trisakti Gedung A2 Lantal 2 Universitas Trisakti, Jalan Kyai Tapa No.1 Grogol, Jakarta Barat, 11440, Indonesia. Email: jeeset_mtp@trisakti.ac.id Phone: +62-21-56959213



JOURNAL OF EARTH ENERGY SCIENCE, ENGINEERING, AND TECHNOLOGY

HOME LOGIN REGISTER SEARCH CURRENT ARCHIVES ANNOUNCEMENTS ABOUT Home > Editorial Team Menu: EDITORIAL TEAM Click here to Submit Chief Editor R. S. Trijana Kartoatmodjo, Universitas Trisakti, Indonesia 1. Author Guideline Scopus Google-Scholar Sinta 2. Focus and Scope Editors Sonny Irawan, Nazarbayev University, Kazakhstan 3. Ethics Statement Scopus 4. Editorial Team Astra Agus Pramana, Universitas Pertamina, Indonesia Scopus Google-Scholar Sinta 5. Reviewer Kartika Fajarwati Hartono, Universitas Trisakti, Indonesia 6. Plagiarism Screening Policy Scopus Google-Scholar Sinta 7. Mailing Address Fidya Varayesi, Universitas Tanri Abeng, Indonesia Scopus Google-Scholar Sinta 8. Unique Visits Lisa Samura, Universitas Trisakti, Indonesia Scopus Google-Scholar Sinta Journal of Earth Energy Science, Engineering, and Technology (JEESET) has been accredited by Ministry of Research and Technology of the Republic of Indonesia No. 85/M/KPT/2020, April 3 2020, as 4th Rank (SINTA 4). In addition, the journal

Journal Template Download Here

has been listed in Index Copernicus International, Publons, Garuda, Crossref, ISJD, Base, PKP Index, Google Scholar, ResearchBib, ISSN, and Indonesia Onesearch. JEESET is an open access journal. The papers of this journal are available in Archives Section and free of charge for everyone to publish, read, and download.

Copyright (c) 2019 Journal of Earth Energy Science, Engineering, and Technology



JOURNAL OF EARTH ENERGY SCIENCE, ENGINEERING, AND TECHNOLOGY

HOME ABOUT LOGIN REGISTER SEARCH CURRENT ARCHIVES ANNOUNCEMENTS	
Home > Archives > Vol 4, No 3 (2021) VOL 4, NO 3 (2021)	Menu:
JEESET VOL. 4 NO. 3 2021	Click here to Submit
DOI: http://dx.doi.org/10.25105/jeeset.v4i3	1. Author Guideline
TABLE OF CONTENTS	2. Focus and Scope
ARTICLES	3. Ethics Statement
Reservoir Quality Assessment Based on The Occurrence of Burial Diagenesis: Sandstone Case Study From Tanjung Formation, Barito Basin, South Kalimantan DOI : 10.25105/jeeset.v4i3.9766	4. Editorial Team
Rosmalia Dita Nugraheni, Eko Widianto	5. Reviewer
10.25105/Jeeset.v4i3.9766 MAstract views: 0 BPDF views: 0	6. Plagarism Screening Policy
The Effect of Biogas Purification Process Using Calcium Oxide-Based Sorbents on the Diffusion Flame Combustion Characteristics DOI: 10.25105/jeeset.v4i3.9712	7. Mailing Address
Dani Hari Tunggal Prasetiyo, Djoko Wahyudi, Allef Muhammad	8. Unique Visits
10.25105/Jeeset.v4i3.9712 M Abstract views: 0 BPDF views: 0	
Evaluation of the Significance of Production Rates in Reduction of Wax Precipitation and Deposition thickness in a flowline DOI: 10.25105/jeeset.v4i3.10681	
Bright Bariakpoa Kinate, Joseph Atubokiki Ajienka, Sunday Sunday Ikiensikimama	
© 10.25105/jeeset.v4/3.10681 M Abstract views = 0 🔤 PDF views = 0	
Analysis of the Zeolite Size Effect on the Content of Chemical Compounds in Acid Activated Natural Zeolite 901 - 10.25105/jeeset.v4(3.10227	
Fadliah Fadliah, Reno Pratiwi, Wiwik Dahani, Riskaviana Kurniawati, Kartika Fajarwati Hartono, Dina Asmaul Chusniyah, Lailatul Wastiyah, Hadi Purnomo	Journal Template Download Here

Analysis of the Zeolite Size Effect on the Content of Chemical Compounds in Acid Activated Natural Zeolite

(Analisis Pengaruh Ukuran Zeolit Terhadap Kandungan Senyawa Kimia Zeolit Alam Teraktivasi Asam)

Fadliah^{1*}, Reno Pratiwi², Wiwik Dahani¹, Riskaviana Kurniawati¹, Kartika Fajarwati Hartono², Dina Asmaul Chusniyah², Lailatul Wastiyah¹, Hadi Purnomo¹

¹Mining Engineering Department, Universitas Trisakti, Indonesia ²Petroleum Engineering Department, Universitas Trisakti, Indonesia

Abstract

One of the zeolite producing areas in Indonesia is Sukabumi. Natural zeolite originating from Sukabumi is composed of three main types of minerals: mordenite, clinoptilolite, and quartz. Zeolite as a catalyst can be improved by carrying out physical and chemical activation processes. Physically the catalyst can be activated by reducing the size of the zeolite through the grinding and sieving method. This physical activation process can increase the surface area of the zeolite. In this study, variations in the size of zeolite 80 mesh and 100 mesh were carried out that chemically activated by the acid activation method through immersion of natural zeolite with HCl and HF from this acid activation process it will increase the acidity of the zeolite. Measurement of functional groups and chemical compounds in activated zeolite using XRF and FTIR. The results of XRF analysis showed that the SiO₂ content in 80 mesh zeolite was 69.5% and in 100 mesh zeolite was 82.1% and the FTIR analysis showed the presence of the C-H alkene functional group at a wavelength of 675-995 cm⁻¹, ring C-H aromatic at a wavelength of 690-900 cm⁻¹, C-O alcohol/ether/carboxylic acid/ester at wavelength 1610-1680 cm⁻¹, functional group is carboxylic acid at a wavelength of 3500-3650 cm⁻¹ and an alcohol monomer/phenol O-H functional group at a wavelength of 3590-3650 cm⁻¹.

Keywords: Zeolite; Activation; Acid; XRF; FTIR

Sari

Salah satu daerah penghasil zeolit di Indonesia adalah sukabumi. Zeolit alam yang berasal dari sukabumi tersusun dari tiga jenis mineral utama yakni mordenit, klinoptilolit dan kuarsa. Zeolit sebagai katalis dapat ditingkatkan kemampuannya dengan melakukan proses aktifasi fisik maupun kimiawi. Secara fisika katalis dapat diaktivasi dengan cara mereduksi ukuran zeolit melalui metode penggerusan dan pengayakan dari proses aktivasi secara fisika ini dapat meningkatkan luas permukaan dari zeolit. Pada penelitian ini dilakukan variasi ukuran zeolite 80 mesh dan 100 mesh yang diaktivasi secara kimia dilakukan dengan metode aktivasi asam melalui perendaman zeolit alam dengan HCl dan HF, dari proses aktivasi secara asam ini akan meningkatkan sifat keasaman dari zeolit. Pengukuran gugus fungsi dan kandungan senyawa kimia pada zeolite yang telah diaktivasi menggunakan XRF dan FTIR. Hasil analisis XRF menunjukkan kandungan SiO₂ pada zeolite ukuran 80 mesh sebesar 69,5% dan pada zeolite ukuran 100 mesh sebesar 82,1%, dan hasil analisis FTIR menunjukkan adanya gugus fungsi C-H alkena pada Panjang gelombang 675-995 cm⁻¹, C-H cincin aromatic pada Panjang gelombang 690-900 cm⁻¹. C-O alcohol/eter/asam karboksilat/ester pada Panjang gelombang 3500-3650 cm⁻¹ dan gugus fungsi O-H alcohol monomer/fenol pada Panjang gelombang 3590-3650 cm⁻¹.

Kata-kata kunci: Zeolit; Aktivasi; Asam; XRF; FTIR

*Corresponding author E-mail: fadliah@trisakti.ac.id

I. INTRODUCTION

Indonesia has a total zeolite deposit of 447,490,160 tons. The potential of zeolite in Indonesia is caused by the location of Indonesia's territory which is in a series of volcanoes which causes geologically Indonesia to have great potential to produce zeolites [1-4].

Natural zeolites are alumina silicate mineral crystals containing cations such as Na, Ca, K, Mg and Fe [5]. These crystals structurally form a threedimensional framework, are acidic and porous in molecular size.

In its application, zeolites can be used as ion exchange agents, adsorbents, molecular filters, and catalysts [6]. The pore structure of the zeolite is filled with exchangeable cations, so that the zeolite has the ability as an ion exchange agent. This can be done by placing the zeolite into a neutral base or salt solution, which causes the cations in the zeolite framework to be replaced by ions in the alkaline/salt solution in equivalent amounts. When the zeolite is brought into contact with an acid solution, the

aluminum is contained in the -frame.

The zeolite used in this study is a natural zeolite originating from Sukabumi which has not been activated so that there are still many impurities. Impurities in the zeolite will reduce the ability of the zeolite to adsorb because the surface is covered by impurities. Zeolites can be activated because of their hollow 3-dimensional structure. Zeolite can be activated both physical and chemical properties. The physical properties of zeolite can be changed through a heating process to remove water content from the zeolite structure. While the chemical properties of zeolite can be changed by removing impurities from the surface of the zeolite by reacting the zeolite with acid [7].

Several researchers have previously activated zeolite with the addition of transition metals using the addition of Ni-Cr/natural zeolite metal and showed research results in the form of increasing cracking activity and selectivity of zeolite [8]. In addition utilization of natural zeolite in the process of making biodiesel from palm oil [9]. In this research, an initial study of zeolite activation test will be carried out by immersing zeolite with acid at various sizes of zeolite. After that, FTIR and XRF tests were carried out to see the effect of size variations on the content of chemical compounds in the zeolite.

The surface area and acidic properties of zeolite make zeolite easier to change on the surface. For the performance of the zeolite as expected, it is necessary to activate the zeolite to condition it according to its designation. Zeolite can be activated both physical and chemical properties. The physical properties of zeolite can be changed through a heating process to remove water content from the zeolite structure. While the chemical properties of zeolite can be changed by removing impurities from the surface of the zeolite by reacting the zeolite with acid [10]. Zeolite is reacted with acid compounds through an immersion process for a while until the impurities are gone and rinsed until a neutral test result is obtained, after the zeolite is neutral, then the activated zeolite is dried.

The empty space in the zeolite cavity causes zeolite to be used as a catalyst [11]. In the process of using zeolite as a catalyst, the diffusion process occurs in an empty space on the surface [12]. The effectiveness of zeolites has also been shown to be applicable to isomerization activities, addition of alkyl hydrocarbons and petroleum cracking processes [13].

The variables observed included the effect of differences in the size of the zeolite on the content of chemical compounds in the zeolite. The observed characteristics include wavelength shift, zeolite crystallinity, chemical composition and Si/Al ratio in the zeolite. Natural zeolite as the raw material used is sourced from Sukabumi and is raw, not yet activated. Data collection was carried out at the Chemical Laboratory, Faculty of Earth and Energy Technology, Trisakti University, Jakarta.

II. METHOD

The zeolite used is natural zeolite obtained from Sukabumi. Preparations were carried out to condition the zeolite to have a larger volume and surface area, as well as the expected acidity and Si/Al ratio. These activities include washing, filtering, drying and calcining. The zeolite activation process is carried out by being activated by acid by adding HCl and HF as shown in Figure 1 [14–15].



Figure 1. Research Procedure

The procedure of physical and chemical activation of natural zeolite was as follows:

1. Zeolite Size Reduction

Zeolite was ground to produce smaller grain sizes using a mortar and stamper. After that, the zeolite grains were filtered using a sieve. The sieves used were 80 mesh and 100 mesh.

2. Zeolite Immersion and Filtration

The washing was carried out using distilled water for 3 repetitions, then filtered for further drying at a temperature of 120 °C for 2 hours. A total of 100 grams of natural zeolite were immersed in 1% (v/v) HF solution for 30 minutes. After being washed with distilled water to a neutral pH, the zeolite was filtered and dried in the sun to dry.

3. Zeolite Reflux

The zeolite was refluxed in 6 M HCl for 5 hours, at an operating temperature of 60 °C, with continuous stirring.

4. Zeolite Drying

After being filtered and washed with distilled water until the pH of the filtrate was neutral, the zeolite was dried in an oven at 130 °C for 3 hours. After drying soaked in 1% HF solution for 30 minutes.

Washing and neutralization using distilled water was again carried out until the pH of the filtrate was neutral. Zeolite was dried in an oven at 130 °C for 3 hours. Calcination was carried out in a furnace at a temperature of 450 °C, in order to obtain Na-Z (natural sodium zeolite).

Zeolite heating was carried out to evaporate the water particles contained in the zeolite cavities. In the presence of heating, the water will evaporate and increase the catalytic ability of the zeolite.

The catalytic ability and increased surface area make the zeolite easier to react and adsorb other elements. In addition, heating can also cause the structure of the zeolite to be stronger with the evaporation of water and the chemical bonds in the zeolite are getting stronger.

The prepared zeolites were analyzed for characteristics to determine the content of chemical components using XRF (X-Ray Fluorescence), to determine functional groups using FTIR (Fourier-Transform Infrared Spectrometer).



(a) Milled Zeolite



(b) Zeolite Sifting

Figure 2. Zeolite Size Reduction



(a) Zeolite



(b) Zeolite Figure 3. Zeolite Immersion and Filtration



Figure 4. Zeolite Reflux pISSN: 2615-3653

eISSN: 2614-0268



Figure 5. Zeolite Drying

III. RESULTS AND DISCUSSION

Zeolite activation process is carried out both physically and chemically. The analysis of the results of the activation and characterization of zeolite is as follows.

3.1 Physical Activation Process

The Physical Activation process is in the form of reducing the size of the zeolite by grinding and sifting with various sizes, in this case the size of 80 and 100 Mesh is used which serves to see how the effect of size on the zeolite activation process.

Zeolites are aluminasilicate crystals. The constituent components of zeolite consist of three components, namely cations as the first component that can be exchanged on its surface with other cations and if heated it will increase the proton donor ability of the zeolite which causes the zeolite's catalytic activity to increase, alumina silicate framework and water content. In addition, zeolite also has a microporous structure which causes a large zeolite surface area. This causes the zeolite to have a place that can be used in the reaction process. Another characteristic of zeolite is its hydrophobic nature, which indicates that zeolite is difficult to dissolve in water due to the presence of high Si/Al content. The hydrophobicity causes the reactants to diffuse rapidly.

Physical activation serves to increase the surface area of natural zeolite by reducing its size. The larger the surface area of a zeolite, the more the catalytic reaction will increase because more reactants can enter the pores. In addition, physical activation can be done by heating the zeolite so that the water trapped in the pores of the zeolite can evaporate and cause the surface of the pores to increase.

3.2 Chemical Activation Process

The chemical activation process is in the form of acid activation by immersing it with HCl and HF. Soaking with this acid serves to increase acidity, clean the surface of the pores, remove impurities and can also rearrange the position of the atoms that are exchanged and clean the zeolite from impurities which can increase the catalytic activity of the zeolite.

The acidity of a catalyst can be viewed from the understanding of acids and bases according to Bronsted and Lewis. Bronsted stated that the acidity of a catalyst is determined by the ability of the catalyst to form protons or proton donors, whereas according to Lewis, a compound or catalyst can act as an acid if it can accept a free pair of electrons from a base molecule. accepts a pair of electrons and binds them chemically to the catalyst surface. The addition of acidity to the catalyst aims to increase the catalytic activity of the catalyst. The increase in catalytic activity is influenced by the Si/Al ratio which increases with increasing acidity.

3.3 Zeolite Characterization

Zeolite characterization was carried out by analyzing the results of zeolite activation with XRF and FTIR.

The FTIR test was carried out to see the functional groups contained in the sample. The movement of the graph peaks and the intensity of the graph on the FTIR show the difference in absorption in the sample. In this study, the samples were differentiated based on the sample size, namely 80 and 100 mesh.

From Figure 6, it is known that a peak appears at the wavelength of 675-995 cm⁻¹ which indicates the presence of the C-H alkene functional group which usually appears at wavelengths of 3010-3095 and 675-995 cm⁻¹. Then a peak appears at a wavelength of 690-900 cm⁻¹ which indicates the presence of an aromatic ring C-H functional group that appears at a wavelength of 3010-3100 and 690-900 cm⁻¹. Then a peak appears at a wavelength of 1050-1300 cm⁻¹ which indicates the presence of a C-O alcohol/ether/carboxylic acid/ester functional group that appears at that wavelength. Then a peak appears at a wavelength of 1610-1680 cm⁻¹ which indicates the presence of a C=C alkene functional group that appears at that wavelength. Then it appears at a wavelength of 3500-3650 cm⁻¹ which indicates the presence of a monomeric carboxylic acid O-H functional group that appears at that wavelength. Then at a wavelength of 3590-3650 cm⁻¹ which indicates the presence of the O-H alcohol monomer/phenol functional group which usually appears at that wavelength.

XRF test was performed on samples with a size of 80 mesh and 100 mesh. XRF tests were carried out on both samples in elemental and oxide forms. This is done to see how the percentages of elements at different sizes compare.



Figure 6. Natural Zeolite FTIR Test Results

Table 1. Comparison of Chemical Element Content between 80 Mesh Size Zeolite and 100 Mesh

No	Com- ponent	Zeolit 80 Mesh Chemical Ele- ment Content(%)	Zeolit 100 Mesh Chemical Ele- ment Content(%)
1	Al	9.1	0
2	Si	55.9	65.8
3	K	11.2	13.9
4	Ca	9.59	8.62
5	Fe	11.9	9.81

Different particle sizes cause the content of chemical elements in zeolite is also different. This is due to the difference in the surface area of the zeolite. There is a chemical element content that increases with increasing particle size and conversely there is an elemental content that decreases.



Figure 7. The Content of Chemical Elements which Increases with Increasing Size



Figure 8. The Content of Chemical Elements which Decreases with Increasing Size

The content of Si and K elements increased with increasing sample size while the content of Al, Ca, and Fe elements decreased with increasing sample size. This is influenced by differences in the surface area of the sample so that it can increase the acquisition of elements, the smaller the size, the larger the surface area. While the elements that experience a decrease can be caused by the dissolved elements along with impurities.

eISSN: 2614-0268

Table 2.	Comparison	Oxide	Compound	Content	between
	80 Mesh An	d 100 M	lesh Size Ze	eolite	

No	Com- ponent	Zeolite 80 Mesh Oxides Content (%)	Zeolite 100 Mesh Oxides Content (%)
1	Al ₂ O ₃	11	0
2	SiO ₂	69.5	82.1
3	K ₂ O	6.15	7.21
4	CaO	5.63	4.73
5	Fe ₂ O ₃	6.42	5.01



Figure 9. The Content of Oxide Compound which Increases with Increasing Size



Figure 10. The Content of Oxide Compound which Decreases with Increasing Size

In addition to analyzing the content of zeolite in elemental form, measurements of the content of eISSN: 2614-0268 bonded elements or elements in the form of oxides were also carried out. Oxide compounds are the occurrence of elemental bonds in the zeolite with oxygen. The same results were shown by XRF measurements of oxide compounds, namely differences in zeolite particle size resulted in differences in the content of oxide compounds.

The results of measurements of compounds contained in zeolite in the form of oxides show the same results as the measurement of elements that have different content for the size of 80 mesh with 100 mesh. The content of SiO₂ and K₂O compounds increased in percentage while Al₂O₃, CaO and Fe₂O₃ compounds decreased.

IV. CONCLUSIONS

Based on analysis and discussion, several conclusions are obtained as follows:

- The FTIR analysis showed the presence of the C-H alkene functional group at a wavelength of 675-995 cm⁻¹, ring C-H aromatic at a wavelength of 690-900 cm⁻¹, C-O alcohol/ether/carboxylic acid/ester at wavelength 1610-1680 cm⁻¹, functional group C=C alkene 1610-1680 cm⁻¹, the O-H functional group is carboxylic acid at a wavelength of 3500-3650 cm⁻¹ and an alcohol monomer/phenol O-H functional group at a wavelength of 3590-3650 cm⁻¹.
- 2. The content of chemical elements and oxide compounds in zeolite has a difference with the difference in size. Si and K elements increased with increasing sample size while the content of Al, Ca, and Fe elements decreased with decreasing sample size. For oxide compounds SiO₂ and K₂O elements increased with increasing sample size while the content of Al₂O₃, CaO, and Fe₂O₃ decreased with decreasing sample size.

ACKNOWLEDGEMENT

Support from various parties has made research activities run smoothly and well. We thank the Trisakti University Research Institute for providing support so that research on acid activation of zeolite can be carried out properly. We would also like to thank the Faculty of Earth and Energy Technology, Trisakti University, which has provided financial support so that this research can be carried out.

REFERENCES

- [1] Kusdarto, 2008, Potensi Zeolit Indonesia, Jurnal Zeolit Indonesia, VII(2), 78-8.
- [2] Atikah, W.S. 2017. Potensi Zeolit Alam Gunung Kidul Teraktivasi Sebagai Media Adsorben Pewarna Tekstil. Arena Tekstil, 32 (1), 17-24.

https://doi.org/10.31266/at.v32i1.2650

[3] Cadar, O., Senila, M., Hoaghia, M.A., Scurtu,

D., Miu, I., and Levei, E.A. 2020. Effects of Thermal Treatment on NaturalClinoptilolite-Rich Zeolite Behavior in SimulatedBiological Fluids. Molecules, 25, 2570, 1-12. https://doi.org/10.3390/molecules25112570

- [4] Las, T. and Zamroni, H. 2002. Penggunaan Zeolit Dalam Bidang Industri dan Lingkungan. Jurnal Zeolit Indonesia, 1 (1), 27 – 34.
- [5] Ginting, A.Br., Dian, A., Sutri, I., dan Kriswarini, 2007, Karakterisasi Komposisi Kimia, Luas Permukaan Pori dan Sifat Termal dari Zeolit Bayah, Tasikmalaya dan Lampung, J.Tek. Bhn. Nukl. 3(1), 1-48.
- [6] Windarti, T., dan Ahmad, S., 2004, Preparasi Katalis Zeolit Alam Sebagai Katalis dalam Proses Pirolisis Katalitik Polietilena, J. Kim. Sains & Apl. VII(3), 72-77. https://doi.org/10.14710/jksa.7.3.72-77
- [7] Juniansyah, R., Dede, S dan Eko, P.H., 2017, Studi Transformasi Zeolit Alam Asal Sukabumi dengan Menggunakan Air Zamzam Sebagai Sumber Akuades, al-Kimiya, 4(1), 23-30.

https://doi.org/10.15575/ak.v4i1.5080

- [8] Sibarani, K. Z., 2012, Preparasi, Karakterisasi, dan Uji Aktivitas Katalis Ni-Cr/Zeolit Alam pada Proses Perengkahan Limbah Plastik menjadi Fraksi Bensin, Fakultas MIPA Universitas Indonesia.
- [9] Kusuma, R. I., Johan, P. H., Aning, A dan Suraydi, I., 2011, Pemanfaatan Zeolit Alam sebagai Katalis Murah dalam Proses Pembuatan Biodiesel dari Minyak Kelapa Sawit, Prosiding Seminar Nasional Fundamental dan Aplikasi Teknik Kimia 2011, Institut Teknologi Sepuluh Nopember.
- [10] Buchori, L dan Budiyono, 2003, Aktivasi Zeolit dengan Menggunakan Perlakuan Asam dan Kalsinasi, Seminar Nasional Teknik Kimia Indonesia.
- [11] Setiadi, S., M. Nasikin., T. Tsutsui dan T. Kojima., 2008, Change in Catalytic Activity on Acetone Conversion to Aromatic Chemicals Using H-ZSM-5, Proceeding of the International Seminar on Chemistry 2008, pp 464-468.
- [12] Setiadi dan Pertiwi, A., 2007, Preparasi dan Karakterisasi Zeolit Alam untuk Konversi Senyawa ABE menjadi Hidrokarbon, Prosiding Kongres dan Simposium Nasional Kedua MKIS.
- [13] Ermawati, R., Bumiarto, N.J., Irma, R., Eva, O., da, Siti, N., 2016, Pengaruh Residue Catalytic Cracking (RCC) dan Zeolit terhadap Kualitas Crude Oil Hasil Pirolisis Limbah Plastik Polietilena, Jurnal Kimia dan Kemasan, 38 (1), 47 – 54. https://doi.org/10.24817/jkk.v38i1.1978
- [14] Ahmadi, K. and Mushollaeni, W. Aktivasi

Kimiawi Zeolit Alam Untuk Pemurnian Minyak Ikan Dari Hasil Samping Penepungan Ikan Lemuru (Sardinella longiceps). Jurnal Teknologi Pertanian, 8 (2), 71 – 79

[15] Nurliati, G., Krisnandi, Y.K., Sihombing, R., and Salimin, Z. 2015. Studies of Modification of Zeolite by Tandem Acid-Base Treatments and its Adsorptions Performance Towards Thorium. Atom Indonesia, 41(2), 87–95. https://doi.org/10.17146/aij.2015.382

Analysis oftheZeolite Size Effect on the Content of Chemical Compounds in Acid Activated Natural Zeolite

by Reno Pratiwi FTKE

Submission date: 10-Mar-2024 11:25PM (UTC+0700) Submission ID: 2316608749 File name: document_1_.pdf (601.58K) Word count: 3875 Character count: 20435

Analysis of the Zeolite Size Effect on the Content of Chemical Compounds in Acid Activated Natural Zeolite

(Analisis Pengaruh Ukuran Zeolit Terhadap Kandungan Senyawa Kimia Zeolit Alam Teraktivasi Asam)

Fadliah^{1*}, Reno Pratiwi², Wiwik Dahani¹, Riskaviana Kurniawati¹, Kartika Fajarwati Hartono², Dina Asmaul Chusniyah², Lailatul Wastiyah¹, Hadi Purnomo¹

¹Mining Engineering Department, Universitas Trisakti, Indonesia ²Petroleum Engineering Department, Universitas Trisakti, Indonesia

Abstract

One of the zeolite producing areas in Indonesia is Sukabumi. Natural zeolite originating from Sukabumi is composed of three main types of minerals: mordenite, clinoptilolite, and quartz. Zeolite as a catalyst can be improved by carrying out physical and chemical activation processes. Physically the catalyst can be activated by reducing the size of the zeolite. In this study, variations in the size of zeolite 80 mesh and 100 mesh were carried out that chemically activated by the acid activation method through immersion of natural zeolite with HCl and HF from this acid activation process it will increase the acidity of the zeolite. In this study, variations of functional groups and chemical compounds in activated zeolite using XRF and FTIR. The results of XRF analysis showed that the SiO2 content in 80 mesh zeolite was 69.5% and in 100 mesh zeolite was 82.1% and the FTIR analysis showed the presence of the C-H alkene functional group at a wavelength of 675-995 cm⁻¹, functional group C=C alkene 1610-1680 cm⁻¹, the O-H functional group is carboxylic acid ester at wavelength of 3500-3650 cm⁻¹ and an alcohol

Keywords: Zeolite; Activation; Acid; XRF; FTIR

Sari

Salah satu daerah penghasil zeolit di Indonesia adalah sukabumi. Zeolit alam yang berasal dari sukabumi tersusun dari tiga jenis mineral utama yakni mordenit, klinoptilolit dan kuarsa. Zeolit sebagai katalis dapat ditingkatkan kemampuannya dengan melakukan proses aktifasi fisik maupun kimiawi. Secara fisika katalis dapat diaktivasi dengan cara mereduksi ukuran zeolit melalui metode penggerusan dan pengayakan dari proses aktivasi secara fisika ini dapat meningkatkan luas permukaan dari zeolit. Pada penelitian ini dilakukan variasi ukuran zeolite 80 mesh dan 100 mesh yang diaktivasi secara asam ini akan dengan metode aktivasi asam melalui perendaman zeolit alam dengan HCI dan HF, dari proses aktivasi secara asam ini akan meningkatkan sifat keasaman dari zeolit. Pengukuran gugus fungsi dan kandungan senyawa kimia pada zeolite yang telah diaktivasi menggunakan XRF dan FTIR. Hasil analisis XRF menunjukkan kandungan SiO₂ pada zeolite ukuran 80 mesh sebesar 69,5% dan pada zeolite ukuran 100 mesh sebesar 82,1%, dan hasil analisis FTIR menunjukkan adanya gugus fungsi C-H alkena pada Panjang gelombang 675-995 cm⁻¹, C-H cincin aromatic pada Panjang gelombang 690-900 cm⁻¹. C-O alcohol/eter/asam karboksilat/ester pada Panjang gelombang 1610-1680 cm⁻¹, gugus fungsi C-L alkena 1610-1680 cm⁻¹. Gugus fungsi O-H asam karboksilat pada Panjang gelombang 3500-3650 cm⁻¹ dan gugus fungsi O-H alcohol monomer/fenol pada Panjang gelombang 3590-3650 cm⁻¹.

Kata-kata kunci: Zeolit; Aktivasi; Asam; XRF; FTIR

*Corresponding author E-mail: fadliah@trisakti.ac.id

I. INTRODUCTION

Indonesia has a total zeolite deposit of 447,490,160 tons. The potential of zeolite in Indonesia is caused by the location of Indonesia's territory which is in a series of volcances which causes geologically Indonesia to have great potential to produce zeolites [1-4].

Natural zeolites are alumina silicate mineral crystals containing cations such as Na, Ca, K, Mg and Fe [5]. These crystals structurally form a threedimensional framework, are acidic and porous in

eISSN: 2614-0268

molecular size.

In its application, zeolites can be used as ion exchange agents, adsorbents, molecular filters, and catalysts [6]. The pore structure of the zeolite is filled with exchangeable cations, so that the zeolite has the ability as an ion exchange agent. This can be done by placing the zeolite into a neutral base or salt solution, which causes the cations in the zeolite framework to be replaced by ions in the alkaline/salt solution in equivalent amounts. When the zeolite is brought into contact with an acid solution, the

102

aluminum is contained in the -frame.

The zeolite used in this study is a natural zeolite originating from Sukabumi which has not been activated so that there are still many impurities. Impurities in the zeolite will reduce the ability of the zeolite to adsorb because the surface is covered by impurities. Zeolites can be activated because of their hollow 3-dimensional structure. Zeolite can be activated both physical and chemical properties. The physical properties of zeolite can be changed through a heating process to remove water content from the zeolite structure. While the chemical properties of zeolite can be changed by removing impurities from the surface of the zeolite by reacting the zeolite with acid [7].

Several researchers have previously activated zeolite with the addition of transition metals using the addition of Ni-Cr/natural zeolite metal and showed research results in the form of increasing cracking activity and selectivity of zeolite [8]. In addition utilization of natural zeolite in the process of making biodiesel from palm oil [9]. In this research, an initial study of zeolite activation test will be carried out by immersing zeolite with acid at various sizes of zeolite. After that, FTIR and XRF tests were carried out to see the effect of size variations on the content of chemical compounds in the zeolite.

The surface area and acidic properties of zeolite make zeolite easier to change on the surface. For the performance of the zeolite as expected, it is necessary to activate the zeolite to condition it according to its designation. Zeolite can be activated both physical and chemical properties. The physical properties of zeolite can be changed through a heating process to remove water content from the zeolite structure. While the chemical properties of zeolite can be changed by removing impurities from the surface of the zeolite by reacting the zeolite with acid [10]. Zeolite is reacted with acid compounds through an immersion process for a while until the impurities are gone and rinsed until a neutral test result is obtained, after the zeolite is neutral, then the activated zeolite is dried.

The empty space in the zeolite cavity causes zeolite to be used as a catalyst [11]. In the process of using zeolite as a catalyst, the diffusion process occurs in an empty space on the surface [12]. The effectiveness of zeolites has also been shown to be applicable to isomerization activities, addition of alkyl hydrocarbons and petroleum cracking processes [13].

The variables observed included the effect of differences in the size of the zeolite on the content of chemical compounds in the zeolite. The observed characteristics include wavelength shift, zeolite crystallinity, chemical composition and Si/Al ratio in the zeolite. Natural zeolite as the raw material used is sourced from Sukabumi and is raw, not yet

eISSN: 2614-0268

activated. Data collection was carried out at the Chemical Laboratory, Faculty of Earth and Energy Technology, Trisakti University, Jakarta.

II. METHOD

The zeolite used is natural zeolite obtained from Sukabumi. Preparations were carried out to condition the zeolite to have a larger volume and surface area, as well as the expected acidity and Si/Al ratio. These activities include washing, filtering, drying and calcining. The zeolite activation process is carried out by being activated by acid by adding HCl and HF as shown in Figure 1 [14–15].



Figure 1. Research Procedure

The procedure of physical and chemical activation of natural zeolite was as follows:

1. Zeolite Size Reduction

Zeolite was ground to produce smaller grain sizes using a mortar and stamper. After that, the zeolite grains were filtered using a sieve. The sieves used were 80 mesh and 100 mesh.

2. Zeolite Immersion and Filtration

The washing was carried out using distilled water for 3 repetitions, then filtered for further drying at a temperature of 120 °C for 2 hours. A total of 100 grams of natural zeolite were immersed in 1% (v/v) HF solution for 30 minutes. After being washed with distilled water to a neutral pH, the zeolite was filtered and dried in the sun to dry.

3. Zeolite Reflux

The zeolite was refluxed in 6 M HCl for 5 hours, at an operating temperature of 60 $^{\circ}$ C, with continuous stirring.

4. Zeolite Drying

After being filtered and washed with distilled water until the pH of the filtrate was neutral, the zeolite was dried in an oven at 130 °C for 3 hours. After drying soaked in 1% HF solution for 30 minutes.

Washing and neutralization using distilled water was again carried out until the pH of the filtrate was neutral. Zeolite was dried in an oven at 130 °C for 3 hours. Calcination was carried out in a furnace at a temperature of 450 °C, in order to obtain Na-Z (natural sodium zeolite).

Zeolite heating was carried out to evaporate the water particles contained in the zeolite cavities. In the presence of heating, the water will evaporate and increase the catalytic ability of the zeolite.

The catalytic ability and increased surface area make the zeolite easier to react and adsorb other elements. In addition, heating can also cause the structure of the zeolite to be stronger with the evaporation of water and the chemical bonds in the zeolite are getting stronger.

The prepared zeolites were analyzed for characteristics to determine the content of chemical components using XRF (X-Ray Fluorescence), to determine functional groups using FTIR (Fourier-Transform Infrared Spectrometer).



(a) Milled Zeolite



(b) Zeolite Sifting

Figure 2. Zeolite Size Reduction

eISSN: 2614-0268



(a) Zeolite



(b) Zeolite Figure 3. Zeolite Immersion and Filtration



Figure 4. Zeolite Reflux pISSN: 2615-3653

104



Figure 5. Zeolite Drying

III. RESULTS AND DISCUSSION

Zeolite activation process is carried out both physically and chemically. The analysis of the results of the activation and characterization of zeolite is as follows.

3.1 Physical Activation Process

The Physical Activation process is in the form of reducing the size of the zeolite by grinding and sifting with various sizes, in this case the size of 80 and 100 Mesh is used which serves to see how the effect of size on the zeolite activation process.

Zeolites are aluminasilicate crystals. The constituent components of zeolite consist of three components, namely cations as the first component that can be exchanged on its surface with other cations and if heated it will increase the proton donor ability of the zeolite which causes the zeolite's catalytic activity to increase, alumina silicate framework and water content. In addition, zeolite also has a microporous structure which causes a large zeolite surface area. This causes the zeolite to have a place that can be used in the reaction process. Another characteristic of zeolite is its hydrophobic nature, which indicates that zeolite is difficult to dissolve in water due to the presence of high Si/Al content. The hydrophobicity causes the reactants to diffuse rapidly.

Physical activation serves to increase the surface area of natural zeolite by reducing its size. The larger the surface area of a zeolite, the more the catalytic reaction will increase because more reactants can enter the pores. In addition, physical activation can be done by heating the zeolite so that the water

eISSN: 2614-0268

trapped in the pores of the zeolite can evaporate and cause the surface of the pores to increase.

3.2 Chemical Activation Process

The chemical activation process is in the form of acid activation by immersing it with HCl and HF. Soaking with this acid serves to increase acidity, clean the surface of the pores, remove impurities and can also rearrange the position of the atoms that are exchanged and clean the zeolite from impurities which can increase the catalytic activity of the zeolite.

The acidity of a catalyst can be viewed from the understanding of acids and bases according to Bronsted and Lewis. Bronsted stated that the acidity of a catalyst is determined by the ability of the catalyst to form protons or proton donors, whereas according to Lewis, a compound or catalyst can act as an acid if it can accept a free pair of electrons from a base molecule. accepts a pair of electrons and binds them chemically to the catalyst surface. The addition of acidity to the catalyst aims to increase the catalytic activity of the catalyst. The increase in catalytic activity is influenced by the Si/Al ratio which increases with increasing acidity.

3.3 Zeolite Characterization

Zeolite characterization was carried out by analyzing the results of zeolite activation with XRF and FTIR.

The FTIR test was carried out to see the functional groups contained in the sample. The movement of the graph peaks and the intensity of the graph on the FTIR show the difference in absorption in the sample. In this study, the samples were differentiated based on the sample size, namely 80 and 100 mesh.

From Figure 6, it is known that a peak appears at the wavelength of 675-995 cm⁻¹ which indicates the presence of the C-H alkene functional group which usually appears at wavelengths of 3010-3095 and 675-995 cm⁻¹. Then a peak appears at a wavelength of 690-900 cm⁻¹ which indicates the presence of an aromatic ring C-H functional group that appears at a wavelength of 3010-3100 and 690-900 cm-1. Then a peak appears at a wavelength of 1050-1300 cm⁻¹ which indicates the presence of a C-O alcohol/ether/carboxylic acid/ester functional group that appears at that wavelength. Then a peak appears at a wavelength of 1610-1680 cm-1 which indicates the presence of a C=C alkene functional group that appears at that wavelength. Then it appears at a wavelength of 3500-3650 cm⁻¹ which indicates the presence of a monomeric carboxylic acid O-H functional group that appears at that wavelength. Then at a wavelength of 3590-3650 cm⁻¹ which indicates the presence of the O-H alcohol monomer/phenol functional group which usually appears at that wavelength.

105

XRF test was performed on samples with a size of 80 mesh and 100 mesh. XRF tests were carried out on both samples in elemental and oxide forms. This is done to see how the percentages of elements at different sizes compare.



Figure 6. Natural Zeolite FTIR Test Results

Table 1. Comparison of Chemical Element Content between 80 Mesh Size Zeolite and 100 Mesh

No	Com- ponent	Zeolit 80 Mesh Chemical Ele- ment Content(%)	Zeolit 100 Mesh Chemical Ele- ment Content(%)
1	Al	9.1	0
2	Si	55.9	65.8
3	K	11.2	13.9
4	Ca	9.59	8.62
5	Fe	11.9	9.81

eISSN: 2614-0268

Different particle sizes cause the content of chemical elements in zeolite is also different. This is due to the difference in the surface area of the zeolite. There is a chemical element content that increases with increasing particle size and conversely there is an elemental content that decreases.



Figure 7. The Content of Chemical Elements which Increases with Increasing Size



Figure 8. The Content of Chemical Elements which Decreases with Increasing Size

The content of Si and K elements increased with increasing sample size while the content of Al, Ca, and Fe elements decreased with increasing sample size. This is influenced by differences in the surface area of the sample so that it can increase the acquisition of elements, the smaller the size, the larger the surface area. While the elements that experience a decrease can be caused by the dissolved elements along with impurities.

106

 Table 2. Comparison Oxide Compound Content between

 80 Mesh And 100 Mesh Size Zeolite

	No	Com- ponent	Zeolite 80 Mesh Oxides Content (%)	Zeolite 100 Mesh Oxides Content (%)
	1	Al ₂ O ₃	11	0
	2	SiO ₂	69.5	82.1
	3	K ₂ O	6.15	7.21
	4	CaO	5.63	4.73
ĺ	5	Fe ₂ O ₃	6.42	5.01



Figure 9. The Content of Oxide Compound which Increases with Increasing Size



Figure 10. The Content of Oxide Compound which Decreases with Increasing Size

In addition to analyzing the content of zeolite in elemental form, measurements of the content of eISSN: 2614-0268

bonded elements or elements in the form of oxides were also carried out. Oxide compounds are the occurrence of elemental bonds in the zeolite with oxygen. The same results were shown by XRF measurements of oxide compounds, namely differences in zeolite particle size resulted in differences in the content of oxide compounds.

The results of measurements of compounds contained in zeolite in the form of oxides show the same results as the measurement of elements that have different content for the size of 80 mesh with 100 mesh. The content of SiO₂ and K₂O compounds increased in percentage while Al₂O₃, CaO and Fe₂O₃ compounds decreased.

IV. CONCLUSIONS

Based on analysis and discussion, several conclusions are obtained as follows:

- The FTIR analysis showed the presence of the C-H alkene functional group at a wavelength of 675-995 cm⁻¹, ring C-H aromatic at a wavelength of 690-900 cm⁻¹, C-O alcohol/ether/carboxylic acid/ester at wavelength 1610-1680 cm⁻¹, functional group C=C alkene 1610-1680 cm⁻¹, the O-H functional group is carboxylic acid at a wavelength of 3500-3650 cm⁻¹ and an alcohol monomer/phenol O-H functional group at a wavelength of 3590-3650 cm⁻¹.
- 2. The content of chemical elements and oxide compounds in zeolite has a difference with the difference in size. Si and K elements increased with increasing sample size while the content of Al, Ca, and Fe elements decreased with decreasing sample size. For oxide compounds SiO₂ and K₂O elements increased with increasing sample size while the content of Al₂O₃, CaO, and Fe₂O₃ decreased with decreasing sample size.

ACKNOWLEDGEMENT

Support from various parties has made research activities run smoothly and well. We thank the Trisakti University Research Institute for providing support so that research on acid activation of zeolite can be carried out properly. We would also like to thank the Faculty of Earth and Energy Technology, Trisakti University, which has provided financial support so that this research can be carried out.

REFERENCES

107

- Kusdarto, 2008, Potensi Zeolit Indonesia, Jurnal Zeolit Indonesia, VII(2), 78-8.
- [2] Atikah, W.S. 2017. Potensi Zeolit Alam Gunung Kidul Teraktivasi Sebagai Media Adsorben Pewarna Tekstil. Arena Tekstil, 32 (1), 17-24.

https://doi.org/10.31266/at.v32i1.2650 [3] Cadar, O., Senila, M., Hoaghia, M.A., Scurtu,

D., Miu, I., and Levei, E.A. 2020. Effects of Thermal Treatment on NaturalClinoptilolite-Rich Zeolite Behavior in SimulatedBiological Fluids. Molecules, 25, 2570, 1-12. https://doi.org/10.3390/molecules25112570

[4] Las, T. and Zamroni, H. 2002. Penggunaan Zeolit Dalam Bidang Industri dan Lingkungan. Jurnal Zeolit Indonesia, 1 (1), 27 – 34.

- [5] Ginting, A.Br., Dian, A., Sutri, I., dan Kriswarini, 2007, Karakterisasi Komposisi Kimia, Luas Permukaan Pori dan Sifat Termal dari Zeolit Bayah, Tasikmalaya dan Lampung, J.Tek, Bhn. Nukl. 3(1), 1-48.
- [6] Windarti, T., dan Ahmad, S., 2004, Preparasi Katalis Zeolit Alam Sebagai Katalis dalam Proses Pirolisis Katalitik Polietilena, J. Kim. Sains & Apl. VII(3), 72-77. https://doi.org/10.14710/jksa.7.3.72-77
- [7] Juniansyah, R., Dede, S dan Eko, P.H., 2017, Studi Transformasi Zeolit Alam Asal Sukabumi dengan Menggunakan Air Zamzam Sebagai Sumber Akuades, al-Kimiya, 4(1), 23-30.

https://doi.org/10.15575/ak.v4i1.5080

- [8] Sibarani, K. Z., 2012, Preparasi, Karakterisasi, dan Uji Aktivitas Katalis Ni-Cr/Zeolit Alam pada Proses Perengkahan Limbah Plastik menjadi Fraksi Bensin, Fakultas MIPA Universitas Indonesia.
- [9] Kusuma, R. I., Johan, P. H., Aning, A dan Suraydi, I., 2011, Pemanfaatan Zeolit Alam sebagai Katalis Murah dalam Proses Pembuatan Biodiesel dari Minyak Kelapa Sawit, Prosiding Seminar Nasional Fundamental dan Aplikasi Teknik Kimia 2011, Institut Teknologi Sepuluh Nopember.
- [10] Buchori, L dan Budiyono, 2003, Aktivasi Zeolit dengan Menggunakan Perlakuan Asam dan Kalsinasi, Seminar Nasional Teknik Kimia Indonesia.
- [11] Setiadi, S., M. Nasikin., T. Tsutsui dan T. Kojima., 2008, Change in Catalytic Activity on Acetone Conversion to Aromatic Chemicals Using H-ZSM-5, Proceeding of the International Seminar on Chemistry 2008, pp 464-468.
- [12] Setiadi dan Pertiwi, A., 2007, Preparasi dan Karakterisasi Zeolit Alam untuk Konversi Senyawa ABE menjadi Hidrokarbon, Prosiding Kongres dan Simposium Nasional Kedua MKIS.
- [13] Ermawati, R., Bumiarto, N.J., Irma, R., Eva, O., da, Siti, N., 2016, Pengaruh Residue Catalytic Cracking (RCC) dan Zeolit terhadap Kualitas Crude Oil Hasil Pirolisis Limbah Plastik Polietilena, Jurnal Kimia dan Kemasan, 38 (1), 47 – 54. https://doi.org/10.24817/jkk.v38i1.1978

[14] Ahmadi, K. and Mushollaeni, W. Aktivasi

eISSN: 2614-0268

Kimiawi Zeolit Alam Untuk Pemurnian Minyak Ikan Dari Hasil Samping Penepungan Ikan Lemuru (Sardinella longiceps). Jurnal Teknologi Pertanian, 8 (2), 71 – 79

[15] Nurliati, G., Krisnandi, Y.K., Sihombing, R., and Salimin, Z. 2015. Studies of Modification of Zeolite by Tandem Acid-Base Treatments and its Adsorptions Performance Towards Thorium. Atom Indonesia, 41(2), 87–95. https://doi.org/10.17146/aij.2015.382

Analysis of the Zeolite Size Effect on the Content of Chemical Compounds in Acid Activated Natural Zeolite

GRADEMARK REPORT

FINAL GRADE	GENERAL COMMENTS
/100	
PAGE 1	
PAGE 2	
PAGE 3	
PAGE 4	
PAGE 5	
PAGE 6	
PAGE 7	