

The Capability of Three Final Irrigation Materials on apical leakage of Bioceramic Sealer Obturation after Calcium Hydroxide Cleaning

by Tien Suwartini FKG

Submission date: 11-Mar-2025 08:16AM (UTC+0700)

Submission ID: 2611236794

File name: SDJ_48_23,_Au_rev_after_review_Chandra.pdf (255.61K)

Word count: 7117

Character count: 36366

The Capability of Three Final Irrigation Materials on apical leakage of Bioceramic Sealer Obturation after Calcium Hydroxide Cleaning

Chandra Kristopano, Tien Suwartini¹

¹Department of Conservative Dentistry, Faculty of Dentistry, Trisakti University – Indonesia

Corresponding Author: Tien Suwartini, Faculty of Dentistry, Trisakti University – Indonesia

Email: tien.s@trisakti.ac.id

ABSTRACT

Background: Obturation is an important step in root canal treatment. Obturation has to result in a tight root canal closure and eliminate all apical and coronal connection pathways. Calcium hydroxide intramedicament residue left behind may interfere with the endodontic sealer penetration, and cause an apical leakage. Chitosan acetate 0.2% has been shown to have antibacterial effects and can remove the smear layer. **Objective:** To determine the effectiveness of different types of final irrigation on the apical seal of bioceramic sealer obturation after calcium hydroxide intramedicament cleaning. **Method:** The study is performed on a sample of lower first premolar teeth that have been prepared and filled with calcium hydroxide intramedicament paste. One week later, calcium hydroxide removal is performed with NaOCl. The samples were divided into 3 groups based on the final irrigation material before obturation: group 1 was irrigated with 2.5% NaOCl, group 2 with 17% EDTA, and group 3 with 0.2% chitosan acetate. All samples have been obturated using the single cone technique and bioceramic sealer, then immersed in Indiana ink. Apical leakage was measured based on the deepest penetration of the dye into the root canal. **Results:** The smallest apical leakage value was the final irrigation group with 0.2% Chitosan Acetate, and the apical leakage value of the 2.5% NaOCl group was the same as 17% EDTA, but there was no statistically significant difference between the three study groups. **Conclusion:** There is no difference in the effectiveness of final irrigation between EDTA 17% and chitosan-acetate 0.2% on the apical seal of bioceramic sealer obturation after calcium hydroxide removal. Chitosan-acetate 0.2% can be used as an alternative as a final irrigation material for root canals after calcium hydroxide intramedicament, in obturation using a bioceramic sealer.

Keywords: Chitosan acetate, EDTA, Bioceramic sealer, Ca(OH)₂, Apical Leakage

Background

The primary goal of endodontic treatment is to remove as much bacteria from the root canal system as possible before establishing a setting in which the remaining organisms are unable to survive.¹ Obturation is an important phase in the procedure of root canal therapy. Obturation should remove all apical and coronal connection paths and create a tight root canal seal.² Poorly hermetic obturation of the root canal is the most common cause of root canal therapy failure. To prevent harmful bacteria from percolating into and out of the root canal, the apical of the root canal is required to be sealed tightly.² The periapical disease is mainly brought on by microorganisms that remain in the root canal. Even though mechanical and chemical root canal cleaning methods have improved over time, no method has yet been able to eliminate all bacteria from the root canal system. As a result, when pulp necrosis or root canal re-treatment occurs, intracanal medications are applied to inactivate the bacteria that remain in the root canal system.^{1,3}

Calcium hydroxide ($\text{Ca}(\text{OH})_2$) is a commonly used material as an intracanal medicament in endodontic treatment due to its biological ability, antimicrobial activity, and ability to inactivate bacterial endotoxins.^{1,3} However, numerous research on the removal of intracanal medications that contained $\text{Ca}(\text{OH})_2$ using chemical and mechanical methods have shown that there is no effective method of completely removing calcium hydroxide from the root canal system. A root canal treatment's long-term prognosis could be affected by incomplete $\text{Ca}(\text{OH})_2$ removal, which could also significantly impact bonding and sealing.³

Obturation of the root canal aims to stop root canal reinfection by forming an adequate seal against bacteria reinfection and their toxin. Solid core material and sealer were the two types of materials employed for canal obturation. There are a lot of various kinds of sealer base materials that exist at present, such as sealers based on silicone, methacrylate, calcium hydroxide, glass ionomer cement, epoxy resin, and zinc oxide eugenol (ZnOE). Manufacturers claim that these sealers are insoluble, radiopaque, aluminum-free, and water-hardenable. The hydrophilic nature of this particular sealer gives it the ability to slightly expand after hardening, enhancing sealing against the root canal wall.³ However, previous research has shown that the number of microleakage in canals filled with bioceramic materials and resins increases with the presence of $\text{Ca}(\text{OH})_2$ intramedicament left behind.^{1,3}

The most common technique used to remove calcium hydroxide is using a primary apical file combined with irrigation using 2.5-5% sodium hypochlorite (NaOCl) solution followed by 17% ethylenediaminetetraacetic acid (EDTA).^{4,5} NaOCl has the advantage of being antibacterial, proteolytic and can dissolve organic tissue. However, NaOCl is unable to remove inorganic tissue from the smear layer on the root canal wall. In addition, NaOCl is toxic to tissues, corrosive, and has a strong odor.⁶ EDTA is frequently used in the clinic and as the gold standard for final irrigation solutions due to its ability to bind to dentine calcium ions, and dissolve inorganic components of the smear layer. However, prolonged application time of EDTA on the dentine wall may cause erosion and reduce dentine microhardness. In addition, EDTA does not have antibacterial properties.^{2,7,8}

Recently, chitosan has been widely researched and utilized in the field of dentistry due to its biocompatibility, biodegradability, bioadhesion, and non-toxic properties. Chitosan is a polysaccharide from chitin, which is obtained from the shells of crustaceans and shrimp, through a process called deacetylation.^{2,9} Chitosan has been used in various fields such as food, cosmetics, biomedicine, and pharmaceuticals. In acidic conditions, chitosan research as an irrigator in the field of dental research is particularly interesting because of the substance's ability to bind (chelate) various metal ions, such as the treatment of dentine tubule infections, direct pulp capping and in tissue regeneration of pulp injuries.¹⁰⁻¹³ On previous studies have shown that chitosan has high antibacterial properties against *Enterococcus faecalis* and *Candida albicans*. Chitosan has a chelation ability so that it can dissolve the smear layer.^{2,14,15}

Root canal irrigation with chitosan acetate on the dentine surface can remove the smear layer and open the dentine tubules with little erosion of the peritubular dentine.¹⁶ Chitosan is an effective chelation material with little change to the root dentine and can be considered a less invasive substitute than 17% EDTA.¹⁷ On previous research showed that the apical seal and bond strength of epoxy sealer after final

irrigation using 0.5% chitosan nanoparticle solution was created by dissolving 0.5 grams of chitosan powder in 1% acetic acid was equivalent to final irrigation with 17% EDTA. An application time of 3 min resulted in greater apical sealing and push-out bond strength than an application time of 1 min.⁷⁷

Previous studies have shown that microleakage in canals obturated with epoxy and bioceramic resins increases in root canals previously treated with Ca(OH)₂ intramedicament. With the increasing use of large tapering file systems and single cone gutta perca obturation techniques using bioceramic sealer, it is necessary to study the effectiveness of final irrigation with chitosan-acetate on the apical sealing of bioceramic sealer obturation after calcium hydroxide intramedicament removal.

Material and Methods

This research is a laboratory experimental with post-treatment with control carried out in the Microbiology Center of Research and Education (MiCore) laboratory at the Teaching Dental and Oral Hospital (RSGM-P), Faculty of Dentistry, Trisakti University, West Jakarta, Indonesia from November to December 2022. This study used a sample of mandibular premolar teeth after extraction of orthodontic treatment with a total of thirty-four teeth taken by random sampling from forty teeth that have been collected. The thirty teeth became the experimental sample group for the final irrigation with each group having ten samples. These samples have been calculated by Lwanga and Lemeshow's formula concerning the bioceramic sealer apical seal research using the clearing tooth technique that had been carried out previously.¹⁹ The four teeth become the control group in this research that divide into two groups control, which are positive control and negative control.

The sample inclusion criteria in this study were teeth that were perfectly formed, had no caries, no calcification, had never had root canal treatment before, had straight roots, the roots of the teeth had grown completely, the apical size was no more than #20 and sample exclusion criteria were teeth that had more than one root canal and apical foramen, teeth that had been treated with root canals, open apex immature teeth, internal/external resorption, caries/cracks/fractures on the root surface, and/or root canal curvature of more than 10°.²⁰

Preparation of 0,2% chitosan acetate

Chitosan acetate (CA) prepared from shrimp shell chitosan (CHIMULTIGUNA Indonesia, *medical grade* DDA 96%). Preparation of acetic acid solution with 99 ml of distilled water and 1 ml of 100% acetic acid to obtain 1% acetic acid solution. A total of 0.2 grams of chitosan was then added to 100 mL of 1% acetic acid solution and stirred using a magnetic stirrer for 2 hours to obtain 0.2% CA.²¹

Preparation of specimens

The collected teeth according to the inclusion criteria were randomly selected 34 teeth to be used in this study. The selected teeth were crowned (decorated) using a diamond disk or a round-end taper to obtain the root length. K-file #10 was inserted into the root canal until it was visible at the main apical foramen, and the working length was determined by subtracting 1 mm from this size.

Root canals were prepared using ProTaper Universal (Dentsply, Maillefer) to F3 (size 30/06). At each file change, the root canal was apically patency with K-file #10 and the root canal was irrigated with 2 mL of 2.5% NaOCl. The final rinse used 1 mL of 5% NaOCl for 60 seconds and 1 mL of 17% EDTA for 60 seconds. Irrigation with a working length of 12 mm, which is 2 mm from the apical foramen with in-out movements, ended with 5 mL of distilled water flushing. The specimen was dried using a paper point and given a calcium hydroxide intramedicament.^{20,22}

Calcium hydroxide application

In this research, 32 tooth samples were filled with an intramedicament calcium hydroxide paste. Using a plastic plate and tip provided by the manufacturer, the sample's complete root canal was filled with Ca(OH)₂ paste (Calcipec, Japan), with the coronal portion of the paste reaching up to 2 mm from the

orifice. The coronal area was then temporarily sealed (to avoid leakage) using zinc oxide eugenol cement. For seven days, tooth samples were kept in an incubator set to 37 °C with 100% humidity by being wrapped in cotton that had been soaked in saline.³

Calcium hydroxide removal

After seven days, the specimens were removed from the incubator, and the Ca(OH)₂ paste in the root canal was removed with K-file #30 to the working length, then the root canal was irrigated with 5 mL of 2.5% NaOCl, rinsed with 5 mL of distilled water and dried with paper points. The 30 tooth samples were randomly grouped into 3 groups and each group received a different final irrigation treatment:

- a) Group 1: Teeth samples were finally irrigated with 1 mL of 2.5% NaOCl for 1 minute.
- b) Group 2: Teeth samples were finally irrigated with 17% EDTA in 1 mL for 1 minute.
- c) Group 3: Teeth samples were finally irrigated with 1 mL of CA for 1 minute.

Before obturation, the root canal is rinsed with as much as 5 mL of distilled water and dried with a paper point.

Obturation of root canals

Thirty teeth samples were obturated with hydraulic compaction single cone technique. A bioceramic sealer (Ceraceal; Meta Biomed, Korea) was applied to the root canal wall using a lentulo with clockwise movement. Guttapercha was coated at the apical third with the bioceramic sealer and placed in the root canal to the working length. Gutta-percha was cut and condensed to 2 mm below the orifice and then covered with an ionomer cement barrier. Mesiodistal and bucco-lingual radiographs were taken to confirm obturation. Specimens were wrapped in moist cotton and stored in a 37°C incubator at 100% humidity for 72 hours.²⁰

All samples were coated with clear fingernail polish for two times, except for the apical 2 mm. Each coat waited for the fingernail polish to dry. All tooth samples were immersed in Indian ink for 72 hours in the same vertical position to ensure homogeneous hydrostatic pressure on all samples. After completion, the samples were washed under running water for 10 minutes and the nail polish layer was removed.

As positive controls in this study were 2 teeth that had been filled with calcium hydroxide but no removal was performed. The negative controls were 2 teeth that were obturated with bioceramic sealer without prior application of calcium hydroxide intramedicament and the entire apical portion was covered with clear fingernail polish.²³

Clearing Technique

Tooth samples were cleared based on a clearing technique similar to that used by previous researcher Hosoya.²⁴ All tooth samples were demineralized using 5% nitric acid in a sealed bottle for 72 hours. The acid was changed every 24 hours and the bottle was agitated occasionally. Demineralized teeth were rinsed using running water, then immersed in distilled water for 6 hours, the liquid was changed every hour.

All the specimens were dehydrated by successive immersion in 70% alcohol solution for 24 hours, 95% alcohol for 2 hours, and 100% alcohol for 2 hours. demineralized tooth samples were air spray dried and then cleared with methyl salicylate.²⁴

Measurement of apical leakage

Using a stereomicroscope with a 10x magnification and a scale of mm, apical leakage in the sample was calculated based on the penetration of black ink in the space between the sealer and the root canal wall. The data gathered is the mean of the data made by two calibrated observers.




Figure 1. (a) Apical leakage from EDTA 17% group (b) Apical leakage from NaOCl 2,5% group (c) Apical leakage from CA 0,2% group (d) Positive control (e) Negative control

Statistical Analysis

Apical leakage data obtained from the results of this study were tested for normality using the Shapiro-Wilk Test. Statistical calculations were performed with SPSS Statistics for Windows software version 25 (IBM, USA). The results showed that the data were not normally distributed ($p < 0.05$). Therefore, a different test analysis was performed using the Kruskal Wallis Non-parametric test analysis to determine the difference in the apical seal of obturation using bioceramic sealer in all final irrigation treatment groups, which are: (1) 2.5% NaOCl final irrigation group, (2) 17% EDTA, and (3) 0.2% CA, with a significance level of $p < 0.05$.

Results

In this research, the effectiveness of the final irrigation solution was tested on the apical leakage of root canals that had previously been given calcium hydroxide intramedicaments and obturated with bioceramic sealer. The results of this study showed that the average value of leakage of NaOCl 2.5% was the same as EDTA 17% (0.03 ± 0.04), and the smallest value of leakage was 0.2% CA solution (0.02 ± 0.04). (Table 1)

The normality test used the Shapiro-Wilk test. The results showed that the leakage value data of the three test materials were not normally distributed ($p < 0.05$). Therefore, the hypothesis test continued with Kruskal-Wallis non-parametric test.

Table.1 Mean and Standard Deviation of Apical Leakage

Group	N	Mean (mm) \pm SD
NaOCl 2,5%	10	$0,03 \pm 0,04$
EDTA 17%	10	$0,03 \pm 0,04$
CA 0,2%	10	$0,02 \pm 0,04$

Based on the Kruskal Wallis test results, the mean value obtained by final irrigation using NaOCl 2.5% (16.00), EDTA (16.00) and CA 0.2% (14.50) which means that NaOCl and EDTA have slightly higher leakage than CA, Kruskal Wallis test results obtained a sig. value of 0.848, that the value $p > 0.05$. Based on the Sig. value, it can be stated that after cleaning calcium hydroxide intramedicament, there is no difference in the final irrigation effectiveness between EDTA and chitosan-acetate. (Table 2)

Table 2. Kruskal Wallis Test

Group	N	Mean	Sig.
Final irrigation using NaOCl 2.5%	10	16,00	
Final irrigation using EDTA 17%	10	16,00	0.848
Final irrigation using CA 0.2%	10	14,50	

Sig>0,05

Discussion

The apical seal of the canal is influenced by the nature of the obturation material used and the cleanliness of the root canal material before obturation.²⁵ Calcium hydroxide has a high pH so it is mostly used for root canal intramedicaments. However, calcium hydroxide is difficult to remove completely from the root canal, it's hinder the penetration of the sealer into the dentine tubules of the root canal and reducing the sealer to the canal wall. This may lead to microleakage in the long term.

This research aims to determine the apical seal of obturation using bioceramic sealer after calcium hydroxide removal with three groups of irrigation materials namely NaOCl 2.5, EDTA 17%, and CA 0.2%. On observation under a stereomicroscope with 10 times magnification, there was no clear penetration of the dye in all samples, therefore the magnification was increased to 40 times. Measurements were taken by two observers with three repetitions each. Based on the results of the analysis, it was found that there was no difference in the effectiveness of final irrigation between EDTA 17% and chitosan-acetate 0.2% on the apical seal of obturation of bioceramic sealer after calcium hydroxide removal. The smallest mean value of apical leakage was the group with final irrigation with 0.2% CA. The apical leakage value of the 2.5% NaOCl group was similar to that of 17% EDTA, but there was no statistically significant difference in the apical leakage value among the three groups.

In this research, the 2.5% NaOCl solution group was used to determine the leakage that occurred in the group that did not use chelation material during the final irrigation before obturation. Based on the research of Basrani, et al. NaOCl irrigation is recommended to be used before bioceramic materials. The results of this research showed that the apical seal of the 2.5% NaOCl irrigation group was equivalent to the group using 17% EDTA chelation material. In root canal obturation using bioceramic sealer, the results of research by Yilirim, et al. and Torabinejad, et al. reported that the presence of a smear layer slightly increased the bond strength of bioceramic sealer to the root canal wall. The moisture contained in the smear layer has been shown to be the same as a hydrophilic bioceramic-based sealer to adapt to dentine and act as a bonding agent between root canal dentine.¹⁶

The group of teeth that were final irrigated with 17% EDTA, in this study showed the same leakage value as the leakage in the group that was final irrigated with 2.5% NaOCl. The results of this study are different from the results of research by Eman, et al., Dr. Prateek, et al., and Doaa, et al. who conducted research without preceding the application of calcium hydroxide, showing that obturation leakage after final irrigation with EDTA was smaller than with NaOCl. EDTA solution can reduce apical leakage because EDTA is more effective in cleaning the smear layer in root canal dentine and allows the penetration of bioceramic silica in the dentine tubules to improve the mechanical retention of the silica and the bonding strength of the silica to the root canal dentine.²⁶⁻²⁸ However, the results of research by Ariani, et al. showed that the apical leakage value after final irrigation with EDTA was greater than that of NaOCl 2.5%. This can be caused because EDTA only dissolves inorganic particles so that organic particles are still left in the root canal. In addition, EDTA also dissolves dentine, causing erosion of peritubular and intratubular dentine, leading to irregularity of dentine structure and thus reducing the seal and adaptation between sealer and dentine. This theory was also proven in a previous study which said that EDTA causes erosion of dentine through the process of demineralization and excessive opening of dentine tubules.^{29,30}

Chitosan is a hydrophilic polymer that adsorbs into root dentine and allows it to penetrate deeper into the dentine tubules. Chitosan consists of higher amounts of hydroxyl and amino groups which make it cationic in nature, allowing ionic interaction with calcium ions from dentine. Chitosan acetate solution at 0.2% concentration following previous studies showed its efficiency in removing the smear layer at this low concentration with minimal dentine erosion.^{12,31}

The results of this study showed that the mean leakage value of 0.2% CA solution was smaller than the NaOCl 2.5% and EDTA 17% groups. These results are supported by the research of Veeramachaneni, et al. which showed that the use of 0.2% chitosan as the final irrigation in bioceramic sealer obturation showed good apical seal. Chitosan is an effective chelating agent with less alteration to the root dentine and can be considered a less invasive substitute for 17% EDTA. Antunes, et al. reported that 0.2% chitosan on the dentine surface removed the smear layer and unblocked the dentine tubules with little erosion of the peritubular dentine.⁵ Based on the research of Medhat, et al. the apical

seal of bioceramic sealer after the use of 0.2% CA as an irrigation solution is slightly better than the use of EDTA.³²

In this research, a single cone obturation procedure with a bioceramic sealer was the method used. The single cone approach has been suggested by previous research to be used for applying bioceramic sealer. Due to the bioceramic sealer's slow hardening period, which gives it more time to expand, the sealer is pushed closer to the dentine wall in the tooth root canal.^{28,33}

The results of this study proved that the minimum leakage in the three tested groups was due to the bioceramic sealer (Ceraseal) having a good chemical attachment to the dentine wall.

The mechanism of the hardening reaction of bioceramic-based sealer starts by absorbing water from the dentine tubules. The freshly mixed bioceramic sealer releases high amounts of Si⁴⁺, Ca⁺⁺, and OH⁻ ions during hardening. This reaction produces the hydrogel calcium silicate and hydroxyapatite. The calcium silicate hydrogel chemically bonds with hydroxyapatite through hydroxyl groups, then the hydroxyapatite in the sealer undergoes a continuous crystal growth process and both sealer compounds form a strong chemical bond with dentine. The sealer also flows within the dentine tubules without shrinkage during hardening, resulting in less micro-leakage on the apical.^{34,35} Previous studies have shown that bioceramic sealers do not shrink during the setting process because they do not contain monomers, thus providing a good sealing capability between the sealer and the dentine walls of the root canal.³⁶

Most research studies on the push-out bond strength after calcium hydroxide treatment are relevant to the quality of obturation. The clinical importance of push-out bond strength values' effects on the efficacy of endodontic treatment, however, is not entirely understood.³⁷ Some research states that the presence of calcium hydroxide can reduce the push-out bond strength of sealer, but other research states that it has no effect. This may be due to differences in research methods.

Previous research has shown that the amount of root canal microleakage with bioceramic sealer increases in the presence of Ca(OH)₂.³ However, in this research, the apical leakage was very small. This research reinforces the results of push-out bond strength studies of bioceramic sealer after calcium hydroxide application conducted by Hegde, et al., Amir, et al., Akcay, et al., and Ustun, et al. which proved that calcium hydroxide had no significant effect on the push out bond strength of various root canal sealer even though the studies used different methods. Ustun et al. used 1% NaOCl irrigation with ultrasonic agitation, Amin et al. used passive ultrasonic irrigation with 2.5% NaOCl and final irrigation with EDTA.^{17, 38-41}

These results are also supported by previous studies showing that residual Ca(OH)₂ can increase the bond strength of bioceramic sealer and improve the release resistance of calcium silicate-based sealer. Residual calcium hydroxide also improves the marginal adaptation of MTA.^{39,42} It is assumed that the residue of Ca(OH)₂ can chemically interact with the bioceramic sealer and have a positive effect on the apical seal in this study. The results of this research are different from the results of research by Araghi, et al. and Ghabraei, et al. who stated that intramedicament Ca(OH)₂ had a negative effect on the apical seal of bioceramic sealer.^{3,37}

In this research, obturation using bioceramic sealer was performed after Ca(OH)₂ removal before obturation the final irrigation was performed using NaOCl, EDTA, and CA irrigation materials which resulted in minimal leakage. There may be other factors that affect the apical seal, such as volume and flow rate during irrigation. The flow rate of irrigation can be influenced by the size of the needle diameter. The use of needles with a smaller size diameter is preferred because it increases the flow rate and shear stress on the root canal walls.^{43,44}

In this study, a manual irrigation technique was used with a 30G side-vented and close-ended irrigation needle as suggested in previous research. The needle was given a stopper 2 mm shorter than the apex and moved in and out at a speed of 5 mL/minute. This movement produces apical pressure with shear stress on the root canal wall so that it can produce better root canal wall cleanliness and does not cause injury to periapical tissues.^{45,46} The results of Ghabraei, et al. showed that there was no significant difference in the effectiveness of Ca(OH)₂ removal using manual and ultrasonic files. Based on observation by Scanning Electron Microscope, both techniques could not remove all Ca(OH)₂ from the root canal wall, but the Ca(OH)₂ left after ultrasonic cleaning was less.³⁷

The positive control group in this study was a dental root canal filled with calcium hydroxide intramedicament. The results showed that Indiana ink dye could penetrate root canals filled with

calcium hydroxide 6 mm and 7 mm apically. This suggests that calcium hydroxide intramedicament is an unstable and soluble material, leaving gaps for the dye to penetrate.

The primary weakness of the research is that it is challenging to calculate the amount of leakage because all groups' leakage during bioceramic obturation is very small and almost unseen under a stereomicroscope with a 10 times magnification. According to various researchers, the dye penetration technique is still regarded as helping identify the micro-leakage rate, however, micro-computed tomography would provide a more precise result.³

The results of this research show that there is no effect of different types of final irrigation materials after calcium hydroxide cleaning towards the apical seal on obturation of bioceramic-based sealer. Further research on the effect of calcium hydroxide cleaning with various solutions and irrigation techniques needs to be carried out to obtain the apical seal of root canal obturation on various types of sealer so that the success of root canal treatment will increase.

Conclusion

The results of this research can be concluded that there is no difference in the effectiveness of the final irrigation between EDTA 17% and chitosan-acetate 0.2% on the apical seal of bioceramic sealer obturation after cleaning calcium hydroxide intramedicament. The smallest apical leakage value is the final irrigation group with CA 0.2% so that it can be used as an alternative as a final irrigation material for root canals after calcium hydroxide intramedicament application in obturation using a bioceramic sealer.

Acknowledgments

The authors would like to thank Dr. drg. Tien Suwartini, Sp.KG., Sub.sp, KE (K) for guiding the research and writing of this article.

Conflict of Interest

The authors declare that there are no conflicts of interest

References

1. Ahmetoğlu F, Keleş A, Şimşek N. Effectiveness of the several irrigation techniques for removal of calcium hydroxide-based intracanal medication from an artificial standardized groove in the apical root canal. *MDJ*. 2013;2:53–6.
2. Enggardipta RA, Untara RTE, Santosa P, Kartikaningtyas AT, Widyastuti A, Ratih DN. Apical sealing ability of chitosan nanoparticles in the epoxy-resin-based endodontic sealer. *MKGI*. 2020;5(2):69.
3. Araghi S, Mirzaee SS, Soltani P, Miri S, Miri M. The effect of calcium hydroxide on the apical microleakage of canals filled with bioceramic and resin sealers. *G Ital Endod*. 2020;34(2):151–6.
4. Shaik JA, Reddy RK. Review article Prevention and treatment of white spot lesions in orthodontic patients. *Contemp Clin Dent*. 2017;8(September):11–9.
5. Veeramachaneni C, Aravelli S, Dungdigalla S. Comparative evaluation of push-out bond strength of bioceramic and epoxy sealers after using various final irrigants: an in vitro study. *J Conserv Dent*. 2022;25(2):145–150.
6. Ali A, Bhosale A, Pawar S, Kakti A, Bichpuriya A, Agwan MA. Current trends in root canal irrigation. *Cureus*. 2022;14(5):1–8.
7. Ayer A, Manandhar TR, Agrawal N, Vikram M, Suwal P. A comparative study of apical microleakage of different root canal sealers by apical dye penetration. *Bangladesh J Med Sci*. 2017;16(2):219–24.

8. Tummala M, Chandrasekhar V, Shashi Rashmi A, Kundabala M, Ballal V. Assessment of the wetting behavior of three different root canal sealers on root canal dentine. *J Conserv Dent.* 2012;15(2):109–12.
9. Mohammadi Z, Shalavi S, Jafarzadeh H. Ethylenediaminetetraacetic acid in endodontics. *Eur J Dent.* 2013;7.
10. Sarkees M, Al-Maarawi K. Chitosan: a natural substitute of EDTA solution for final irrigation in endodontics treatment. *Niger J Clin Pract.* 2e:1070–7.
11. Kong M, Chen XG, Xing K, Park HJ. Antimicrobial properties of chitosan and mode of action: A state of the art review. *Int J Food Microbiol.* 2010;144(1):51–63.
12. Silva PV, Guedes DFC, Pecora JD, Cruz-Filho AM da. Time-dependent effects of chitosan on dentine structures. *Braz Dent J.* 2012;23(4):357–61.
13. Shrestha A, Kishen A. The effect of tissue inhibitors on the antibacterial activity of chitosan nanoparticles and photodynamic therapy. *J Endod.* 2012;38(9):1275–8.
14. Darrag AM. Effectiveness of different final irrigation solutions on smear layer removal in intraradicular dentine. *Tanta Dent J.* 2014;11(2):93–9.
15. Aljebory AM, Alsalman TM, Aljebory A, Alsalman TM. Chitosan nanoparticles: review article. *Imp J Interdiscip Res (IJIR).* 2017;3(7):233–42.
16. Çetinkaya İ, Bodrumlu E, Kocak MM, Kocak S, Sağlam BC, Türker SA. Effect of modified NaOCl irrigation solution on bond strength of bioceramic-based root canal sealer to dentine. *Indian J Dent Res.* 2020;31(4):574–8.
17. Pimenta JA, Zapparoli D, Pécora JD, Cruz-Filho AM. Chitosan: Effect of a new chelating agent on the microhardness of root dentine. *Braz Dent J.* 2012;23(3):212–7.
18. Kartinawanti AT, Khoiruzza Asy'ari A. Penyakit pulpa dan perawatan saluran akar satu kali kunjungan: literature review. *J Ilmu Kedokt Gigi.* 2021;4(2):64–72.
19. Mahpudhah A, Erlita I, Maglenda B, Studi P, Gigi K, Gigi FK, et al. Dentine jurnal kedokteran gigi pengaruh kombinasi larutan irigasi terhadap kekuatan pelekatan sealer resin dan non-resin pada dinding saluran. *J Kedokt Gigi.* 2021;V(1):1–6.
20. Widhihapsari S, Ratri Nari D, Nugraheni T. Perbedaan bahan irigasi akhir saluran akar terhadap kekuatan pelekatan push-out bahan pengisi saluran akar. *J Ked Gi.* 2016;7(2):171–8.
21. Kartynawanty AT, Berliana A. Retreatment atau perawatan ulang saluran akar gigi 11 non vital dengan fistula. *Pros Dent Semin Univ Muhammadiyah Surakarta* 5. 2021;19 – 28.
22. Vula V, Ajeti N, Kuçi A, Stavileci M, Vula V. An in vitro comparative evaluation of apical leakage using different root canal sealers. *Med Sci Monit Basic Res.* 2020;26: e928175.
23. De Carvalho M, Stamford TC., Dos SE, Tenorio P, Sampaio F. Chitosan as an antimicrobial agent. *Sci against Microb Pathog Commun Curr Res Technol Adv.* 2011;32–3.
24. Pérard M, Le Goff A, Le Clerc J, Gautier T, Bertaud-Gounot V, Dautel A. Study of the rinsendo action on the smear layer and debris removal by scanning electron microscopy. *Endo (L Engl).* 2013;7(1):15–21
25. Paul J. Recent trends in irrigation in endodontics. *Int J Curr Microbiol Appl Sci.* 2014;3(12):941–52.
26. Gopikrishna V, Venkateshbabu N, Krithikadatta J, Kandaswamy D. Evaluation of the effect of MTAD in comparison with EDTA when employed as the final rinse on the shear bond strength of three endodontic sealers to dentinee. *Aust Endod J.* 2011;37(1):12–7.
27. Hardani PT, Perwito D, Mayzika NA. Review artikel: isolasi Kitin dan kitosan Dari berbagai sumber ahan alam. *J Sains Farm.* 2021;469–75.
28. Kmiec M, Pighinelli L, Silva MM, Reis VO dos. Chitosan-Properties and Applications in Dentistry. *Adv Tissue Eng Regen Med Open Access.* 2017;2(4).
29. El Zayat S, Fawzy M, Bastawy H. Efficacy of chitosan as root canal irrigant in removing smear layer in curved root canals using endovac irrigation system (SEM Study). *Al-Azhar Dent J Girls.* 2018;5(1):485–94.
30. Gonzalez Gratz GA, Iriarte Guerra MF, Alarcon Goldenberg PE. Efficacy of irrigation techniques in removing calcium hydroxide: a literature review. Vol. (24):1-13, *Odontostomatología;* 2022.
31. Sari AN, Untara TE. Root Canal Retreatment menggunakan Kombinasi Kalsium Hidroksida dan Chlorhexidine sebagai Medikamen Intra Kanal Insisivus Sentral Kiri Maksila. *Maj Kedokt Gigi Indones.* 2014;21(2):165.

32. Kumar A, Tamanna S, Iftekhar H. Intracanal medicaments – Their use in modern endodontics: A narrative review. *J Oral Res Rev.* 2019;11(2):94.
33. Ortega JS, Guerrero J, Elorza H, Luis R, Aranda G. Calcium hydroxide influence and intrachannel medication in apical leakage. *Rev Odontol Mex.* 2011;15(4):224–30.
34. Ricucci D, Langeland K. Incomplete calcium hydroxide removal from the root canal: A case report. *Int Endod J.* 1997;30(6):418–21.
35. Wang Y, Guo LY, Fang HZ, Zou WL, Yang YM, Gao Y, et al. An in vitro study on the efficacy of removing calcium hydroxide from curved root canal systems in root canal therapy. *Int J Oral Sci.* 2017;9(2):110–6.
36. Al-Haddad A, Aziz ZACA. Bioceramic-based root canal sealers: a review. *Int J Biomater.* 2016;2016:1–10.
37. Al-Jawad J. Evaluation of bioceramic sealer apical seal in dry and wet conditions. *J Gen Dent.* 2021;2(6):1–3.
38. Han L, Okiji T. Uptake of calcium and silicon released from calcium silicate-based endodontic materials into root canal dentine. *Int Endod J.* 2011;44(12):1081–7.
39. Atmeh AR, Chong EZ, Richard G, Festy F, Watson TF. Dentine-cement interfacial interaction: Calcium silicates and polyalkenoates. *J Dent Res.* 2012;91(5):454–9.
40. Ghabraei S, Bolhari B, Yaghoobnejad F, Meraji N. Effect of intra-canal calcium hydroxide remnants on the push-out bond strength of two endodontic sealers. *Iran Endod J.* 2017;12(2):168–72.
41. Forough Reyhani M, Ghasemi N, Rahimi S, Salem Milani A, Mokhtari H, Shakouie S, et al. Push-out bond strength of dorifill, epiphany, and mta-fillapex sealers to root canal dentine with and without smear layer. *Iran Endod J.* 2014;9(4):246–50.
42. Lotfi M, Ghasemi N, Rahimi S, Bahari M, Vosoughhosseini S, Saghiri MA, et al. Effect of smear layer on the push-out bond strength of two endodontic biomaterials to radicular dentine. *Iran Endod J.* 2013;9(1):41–4.
43. Veríssimo DM, do Vale MS. Methodologies for assessment of apical and coronal leakage of endodontic filling materials: a critical review. *J Oral Sci.* 2006;48(3):93–8.
44. Kont Çobankara F, Adanir N, Belli S, Pashley DH. A quantitative evaluation of apical leakage of four root-canal sealers. *Int Endod J.* 2002;35(12):979–84.
45. Miletic I, Prpic-Mehicic G, Maršan T, Tambic-Andrasevic A, Pleško S, Karlovic Z, et al. Bacterial and fungal microleakage of AH26 and AH Plus root canal sealers. *Int Endod J.* 2002;35(5):428–32.
46. Pommel L, About I, Pashley D, Camps J. Apical leakage of four endodontic sealers. *J Endod.* 2003;29(3):208–10.
47. Mente J, Ferk S, Dreyhaupt J, Deckert A, Legner M, Staehle HJ. Assessment of different dyes used in leakage studies. *Clin Oral Investig.* 2010;14(3):331–8.
48. Aryanto M, Paath SL. Perbedaan kebocoran mikro antara pengisian saluran akar teknik single cone menggunakan sealer berbasis dasar zinc oxide eugenol dan epoxy resin. *J Kedokt Gigi Univ Padjadjaran.* 2020;32(2):126.
49. Hegde VR, Arora NJ. Dentineal element incorporation, interfacial adaptation, and pH change induced by bioceramic sealer, mineral trioxide aggregate-based sealer, and epoxy resin-based sealer – An in vitro, scanning electron microscopy electron probe X-ray microanalysis study. *Endodontology.* 2020;32(2):76–80.
50. Alalaf N, Alkhalidi e. Comparative assessment of root canal sealer's apical sealing ability. *Al-Rafidain Dent J.* 2022;22(1):124–35.
51. Generali L, Cavani F, Franceschetti F, Sassatelli P, Giardino L, Pirani C, et al. Calcium hydroxide removal using four different irrigation systems: a quantitative evaluation by scanning electron microscopy. *Appl Sci.* 2022;12(1).
52. Nakano M, Yamamoto Y, Misawa A, Yamakawa S, Yoshida T, Yamazaki Y, et al. A comparative evaluation of irrigation methods for calcium hydroxide removal from the root canal: An in vitro study. *Dent Res Oral Heal.* 2021;04(02):25–33.

53. Ok E, Altunsoy M, Tanriver M, Çapar İD. Effectiveness of different irrigation protocols on calcium hydroxide removal from simulated immature teeth after apexification. *Acta Biomater Odontol Scand.* 2015;1(1):1–5.
54. Hosoya N, Nomura M, Yoshikubo A, Arai T, Nakamura J, Cox CF. Effect of canal drying methods on the apical seal. *J Endod.* 2000;26(5):292–4.
55. Awaru BT, Nugroho JJ. Restorasi pada gigi anterior setelah perawatan endodontik. *J Dentomaxillofacial Sci.* 2012;11(3):187.
56. Basrani BR, Malkhassian G. Update on irrigation disinfection. *American association of endodontists.* 2021.
57. Adil E, Qadir A, Sulaiman AR, Abduljawad JA. The sealing ability of bioceramic sealer using different irrigation solutions (a comparative study). 2022;10(6):229–32.
58. Singh P, Mustilwar R, Pathak S, Chhabra H singh, Charulata Sree P, Banik A. An in vitro study of the effects of final irrigation protocols on a new bioceramic sealer. *J Pharm Negat Results.* 2022;13(5):559–63.
59. AlEraky DM, Rahoma AM, Abuhashish HM, AlQasser A, AlHamali A, AlHussain HM, et al. Assessment of the bacterial sealing ability of two different bio-ceramic sealers in single-rooted teeth using single Cone obturation technique: an in vitro study. *Appl Sci.* 2023;13(5).
60. Ariani TN, Zubaidah N, Mudjiono M. The effectiveness of 2.5% NaOCl irrigation and 17% EDTA against the sealing ability of resin paste. *Conserv Dent J.* 2020;9(2):105.
61. Çalt S, Serper A. Time-dependent effects of EDTA on dentine structures. *J Endod.* 2002;28(1):17–9.
62. Anika Mittal, Shifali Dadu, Bidya Yendrebam, Anju Abraham, Neetu Sharma Singh PG. Comparison of new irrigating solutions on smear layer removal and calcium ions chelation from the root canal: An in vitro study. *Endodontology.* 2018;30(1):55–61.
63. Medhat A, Ghoneim A, Nabil Roshdy N. The effect of final irrigation Protocols on the apical sealing ability of epoxy resin-based and bioceramic-based root canal sealers. *Open Access Maced J Med Sci.* 2022;10(D):458–64.
64. Abo El-Mal OE. sealing ability of single cone obturation technique using ultrasonic activation of bioceramic sealer: an in vitro study. *Ahram Can Dent J.* 2023;2(1):1–12.
65. Kour S, Kumar A, Malik A. Apical microleakage comparison using various sealers and different obturation techniques- An in-vitro study. *IP Indian J Conserv Endod.* 2022;7(3):125–9.
66. Manjila JC, Vijay R, Sreekha A, Santhosh L, Reddy J, Srinivasan A. Apical microleakage in root canals with separated rotary instruments obturated with different endodontic sealers. Vol. 25, *JCD.* 2022. p. 274–7.
67. Trope M, Bunes A, Debelian G. Root filling materials and techniques: bioceramics a new hope? *Endod Top.* 2015;32(1):86–96.
68. Hegde V, Arora S. Effect of intracanal medicaments on push-out bond strength of Smart-Seal system. *J Conserv Dent.* 2015;18(5):414–8.
69. Wanees Amin SA, Seyam RS, El-Samman MA. The effect of prior calcium hydroxide intracanal placement on the bond strength of two calcium silicate-based and an epoxy resin-based endodontic sealers. *J Endod.* 2012;38(5):696–9.
70. Akcay M, Arslan H, Topcuoglu HS, Tuncay O. Effect of calcium hydroxide and double and triple antibiotic pastes on the bond strength of epoxy resin-based sealer to root canal dentine. *J Endod.* 2014;40(10):1663–7.
71. Üstün Y, Arslan S, Aslan T. Effects of calcium hydroxide and propolis intracanal medicaments on bond strength of resin-based endodontic sealer as assessed by push-out test. *Dent Mater J.* 2013;32(6):913–9.
72. Fernando J, Zambrano B. The influence of residual calcium hydroxide intracanal medicaments on the bond strength of a bioceramic sealer: in vitro. *Int J Dent Sci Innov Res.* 2021;(466):1–5.
73. Ghalandari M, Malek M, Alizadeh H, Ghalandari F, Mosavi A, Shamshirband S, et al. Effect of needle size and volumetric flow rate on root canal irrigation: a numerical investigation. 2019;(September):1–11.
74. Muryani A, Dharsono HDA, Zuleika Z, Moelyadi MA, Fatriadi F. Velocity and wall shear stress of 18% EDTA irrigation solution flow in the removal of Ca(OH)₂ with computational fluid dynamic analysis. *Padjadjaran J Dent.* 2019;31(1):25.

75. Rajamanickam K, Teja KV, Ramesh S, Choudhari S, Cernera M, Armogida NG, et al. Evaluation of Root Canal Cleanliness on Using a Novel Irrigation Device with an Ultrasonic Activation Technique: An Ex Vivo Study. *Appl Sci.* 2023;13(2).
76. Hu S, Duan L, Wan Q, Wang J. Evaluation of needle movement effect on root canal irrigation using a computational fluid dynamics model. *Biomed Eng Online.* 2019;18(1):1–15
77. Ratih DN, Sari NI, Santosa P, Kaswati NM. Time-dependent effect of chitosan nanoparticles as final irrigation on the apical sealing ability and push-out bond strength of root canal obturation. *International Journal of Dentistry.* 2020 Jul 15;2020.

The Capability of Three Final Irrigation Materials on apical leakage of Bioceramic Sealer Obturation after Calcium Hydroxide Cleaning

ORIGINALITY REPORT

15%

SIMILARITY INDEX

14%

INTERNET SOURCES

14%

PUBLICATIONS

3%

STUDENT PAPERS

MATCH ALL SOURCES (ONLY SELECTED SOURCE PRINTED)

3%

★ Mohammadreza Nabavizadeh, Fereshte Sobhnamayan, Mahdi Sedigh-Shams, Sepideh Liaghat. "Comparison of the push-out bond strength of AH Plus sealer to dentin after using different herbal irrigation solutions as the final rinse", PLOS ONE, 2022

Publication

Exclude quotes On

Exclude matches < 15 words

Exclude bibliography On